





VAPPRO 888 S-KOTE VCI VISCOUS LIQUID

NATO STOCK NUMBER: 6850-32-076-1163

DESCRIPTION

Replacement of corroded steam pipes, steam valves, exhaust manifold and exhaust pipe is very expensive and time consuming.

Vappro 888 – S- Kote an amber viscous coating, specially developed to protect deck steam lines, steam valves manifold, exhaust manifold, exhaust pipe and windlass steam chest from corrosion on sea going vessels.

Vappro 888 – S- Kote withstands higher temperatures for longer periods than any similar product and drastically reduces repair and maintenance cost. It is easily applied by brush and requires only minimal surface preparation. When applied to cold surfaces, it will dry to touch within 36 hours after applying.

FEATURES

- Non-flammable
- Water resistant
- Minimal surface preparation
- Good water displacement properties
- Heat resistant
- UV resistant
- Ease of application
- High heat resistance
- Excellent UV and water displacement properties
- Listed in the NATO MCRL(Master Cross Reference List) with assigned NATO Stock Number: 6850-32-076-1163









RoHS COMPLIANT EUROPEAN COMMUNITY DIRECTIVE 2002/95/EC





Copyright 2007. The details of our products are given completely free of undertaking. Since their application lies outside our control, we cannot accept any liability for the results. User shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.



VAPPRO VCI PRODUCTS





SURFACE PREPARATION

Scrape off lose rust and flaking paint, chip off large rust deposits, sweep or blow with compressed air to remove loose rust and dirt particles, wipe oily deposits off with thinner and ensure that surface are thoroughly dry

DIRECTIONS FOR USE

Surface must be ambient temperature. Degrease surface if required. Apply Vappro S-Kote evenly using a spatula or rubber glove. Allow up to 48 hours before resuming operation of steam pipelines.

AVAILABLE PACKAGING

18 kgs pail

SPECIFICATIONS

Appearance Amber Viscous Liquid

Dry To Touch Within 36 hours

Thickness Application 3-5mm

pH 7 ± 0.5

Coverage 0.5m²/kg

Solid Content (% w/w) 45%

For more information about the product or any technical support, please contact us or our authorized distributor:



HEADQUARTERS, SINGAPORE

Magna International Pte Ltd

10H, Enterprise Road, Singapore 629834. Tel (65) 6788-1228 Fax (65) 6785-1497 Email info@magnachem.com.sg Website http://www.magnachem.com.sg

NORTH AMERICA

1450 Government Road West Kirkland Lake, Ontario P2N 2E9 Canada Tel 1.416 479 9151 Fax 1.888 317 1993 Email magna@vappro.com Website: http://www.vappro.com



Magna and Vappro are registered trademarks of Magna International Pte Ltd.

Copyright 2007. The details of our products are given completely free of undertaking. Since their application lies outside our control, we cannot accept any liability for the results. User shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.